



Product Data

Castrol Spheerol EPL

Bearing grease

Description

Castrol Spheerol™ EPL range of greases are lithium based products containing highly refined mineral oils and fortified with extreme pressure (EP) additives as well as corrosion and oxidation inhibitors. These greases have been formulated with additives that provide good film strength under medium to high loads.

Application

The Spheerol EPL range are general purpose greases designed for plant wide lubrication. The range extends from a NLGI 2 for general purpose bearing lubrication to a NLGI 00 semi-fluid grease suitable for centralised lubrication systems and grease filled gearboxes. These greases provide good protection against rust and corrosion as well as resistance to water wash-out; which makes them particularly suitable for equipment where moist or wet conditions are common.

Advantages

- High mechanical stability – the grease keeps its consistency in service ensuring long lubricant life
- Good adhesion – continuous lubrication and reduced consumption as film stays between lubricated surfaces
- Good water resistance – the grease film remains on the surface even in the presence of water
- Resistant to copper and steel corrosion – helps prevent rust and oxidation on metal surfaces
- Excellent EP and anti-wear properties – protects equipment against extreme loading and helps minimise bearing component wear

Typical Characteristics

Test	Method	Units	EPL 0	EPL 1	EPL 2
Appearance, Visual	-	-	Amber to brown	Amber to brown	Amber to brown
Thickener Type	-	-	Lithium	Lithium	Lithium
Base Oil Type	-	-	Mineral oil	Mineral oil	Mineral oil
NLGI Grade	-	-	0	1	2
Density @ 20°C/68°F	ASTM D1475	g/ml	0.890	0.895	0.900
Worked Penetration, 60 strokes @ 25°C/77°F	ISO 2137 ASTM D217	0.1mm	355-385	310-340	265-295
Dropping Point	ISO 2176 ASTM D2265	°C/°F	170/338	195/383	200/392
Base Oil Viscosity @ 40°C/104°F	ISO 3104 ASTM D 445	mm ² /s	150-200	150-200	150-200
Rust Test, 48 hrs @ 52°C/126°F	ASTM D1743	Rating	Pass	Pass	Pass
Copper Corrosion, 24 hrs, 100°C/212°F	ISO 2160 ASTM D4048	Rating	1b	1b	1b
Four Ball Wear Test (1 hr, 40 kg, 1200 rpm, 75°C/167°F), Scar Diameter	ASTM D2266	mm	0.45	0.45	0.45
Four Ball EP Test, Weld load	ASTM D2596	kg	200	250	250
Water Washout @ 79°C/175°F	ASTM D1264	% loss	NA	7.0	3.5
Bomb Oxidation @ 99°C/210°F, Pressure Drop @100h,	ASTM D942 DIN 51808	Psi	6	6	6
DIN Classification	DIN 51502	-	KP0K-20	KP1K-20	KP2K-20
ISO Classification	ISO 6743/9	-	L-XCBEB 0	L-XBCEB 1	L-XBCEB 2

Subject to usual manufacturing tolerances.

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, relubrication intervals should be monitored closely to ensure all previous lubricant is purged.

Castrol Spheerol EPL
09/10/2006, version 1.0
Castrol Spheerol EPL and the Castrol logo are trademarks of Castrol Limited.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol Ltd products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

Deutsche BP AG – Industrial Lubricants & Services, Erkelenzer Str. 20, 41179 Mönchengladbach
Tel: +49 (0)2161 909-30 Fax: +49 (0)2161 909-481

www.castrol.com/industrial